

AFCONA - 4070



Chemical Composition

Modified polyurethane polymer.

Product general description

High molecular weight polymeric dispersant for deflocculation of all type of pigments.

Product Properties:

AFCONA-4070 is a very effective polymeric dispersant for stabilizing inorganic and organic pigments as well as carbon blacks. It has very good stability performance, through effective steric hindrance, on all type of pigments

This results in:

- improved gloss and DOI
- reduced flooding problems
- higher colour strength
- lower viscosity
- increased jetness of high channel carbon black

AFCONA – 4070 has below special properties and recommended in below systems:

- 1) AFCONA-4070 is an improved version of AFCONA-4060. It gives better pigment stability performance. Furthermore, the viscosity depressing property of AFCONA – 4070 is very strong
- 2) AFCONA-4070 is recommended for all baking paints especially for coil coatings. It also can be used for other resin systems as long as it is compatible.
- 3) AFCONA – 4070 has crystallization at low temperature, below 15° C. Thus an improve version, AFCONA – 4071, is must better in term of anti-crystallization, pigment stability and compatibility with CAB.
- 4) After the introduction of AFCONA – 4071, this is not our main recommended product.

Note: AFCONA – 4070 will become slightly hazy at temperature 5°C and below, but this will not influent the quality.

Product Specification

Active ingredients	29 - 31%
Solvent	Xylene/ /Sec-butanol/PMA
Amine Value	6 - 16 mg KOH/g
Gardner color	Max.6
Flash point	33°C
Appearance	Clear to slightly hazy, yellow liquid

Addition and dosage

Calculation method for the required amount of AFCONA-4070 on pigment:

TiO ₂ :	2 - 3%
Other inorganic pigments :	2 - 4%
Organic pigments :	20 - 40%
Carbon blacks :	20 - 60%

Incorporation

AFCONA-4070 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4070 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

AFCONA Polymers Co., Ltd.

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.